



## INTERNATIONAL JOURNAL OF ENGINEERING SCIENCES & RESEARCH TECHNOLOGY

### A New Approach towards Gas Sensing through A.C. Conductivity of Tin Oxide-Copper Oxide Composite

Alison Christina Fernandez, P.Sakthivel, K. Saravana Kumar, Joe Jesudurai\*

\*Department of Physics, Loyola College, Chennai 600034, India

Department of Nuclear Physics, University of Madras, Guindy Campus, Chennai 600 025, India

[joejesudurai@gmail.com](mailto:joejesudurai@gmail.com)

#### Abstract

Tin oxide- Copper oxide composites were synthesized by a hydrothermal method using tin chloride dihydrate and copper nitrate trihydrate as precursors in different molar ratios. The obtained powders were characterized by X-ray diffraction and dielectric analysis. The average crystallite sizes were determined. The analysis exhibited a tetragonal phase for tin oxide and cubic phase for copper oxide. The microstructure of the composites were examined by the scanning electron microscopy. Optical properties were investigated by a UV-Vis absorption spectrophotometer. Good electrical response of the composites to cigarette smoke was observed in dielectric analysis, holding substantial promise for SnO<sub>2</sub>-CuO as a challenging material for novel sensing applications.

**Keywords:** Cigarette smoke; A.C.Conductivity; hydrothermal; composite; morphology.

#### Introduction

Cigarette smoke has proven to be a major health concern over the past years and it is a complex and reactive mixture containing chemicals that are both toxic and carcinogenic. The literature reveals that cigarette smoke contains more than 5000 chemicals including 90 ingredients that are hazardous [1]. Passive smoking is equally dangerous; non-smokers who breathe in this second hand smoke containing nicotine and other harmful substances on regular basis are susceptible to toxic effects that are absorbed into the body [2].

Metal oxide semiconductors such as tin oxide [SnO<sub>2</sub>] are attractive materials for sensing applications from both the scientific and technological viewpoint [3]. The n-type wide band gap (3.4-4.6eV) semiconductor is known for its high chemical stability, low operating temperature and low resistivity [4, 5]. In addition, this oxide holds the key to understanding the viewpoint of the surface properties because of the dual valency of Sn. In fact, the gas response is stimulated not due to the chemisorbed oxygen causing an increase or decrease in conductivity [6].

Composite materials have novel and distinct properties and more effort has been taken to explore their high performance. Much pioneering research has been done in tin oxide with copper oxide as a catalyst [7]. Cupric oxide is an important p-type semiconductor metal oxide with band gap of 1.2eV [8] with a potential prospective for gas sensors. It is a promising candidate because of its long stability, low power

consumption [7], high specific surface area and good electrochemical activity [9, 10].

Gas Sensing technology is of immense importance and has received significant attention over the past decade. From literature we see that considerable research is going into these sensors, in order to enhance its functioning by improving the features like sensitivity, response and recovery time and stability [11-15]. SnO<sub>2</sub> has been widely studied with respect to sensing and it is known to sense a wide variety of gases [14, 16-18]. Tailoring this oxide with other metal oxides like CuO and ZnO and studying the sensitivity has been reported [19-22]. There has been to a great extent reported work on the SnO<sub>2</sub>-CuO composite and its sensitivity to various gases [19,20,23,24]. The general procedure is to measure the sensitivity of the sample to the respective gas through the change in resistance [11,24]; we have taken up an innovative method of studying the a.c.conductivity response of the composite to cigarette smoke.

In the present work, the tin oxide-copper oxide composites were prepared by the hydrothermal method and characterized by XRD, SEM, UV and Dielectric analysis. The crystal structure and crystallite size of the composites have been reported and their morphology have been observed. The optical band gap has been determined. In addition, the electrical response of the composites to cigarette smoke was investigated which is a decisive factor for sensitive sensor fabrication.

### Experimental

The composites were prepared by adding  $\text{Cu}(\text{NO}_3)_2 \cdot 2\text{H}_2\text{O}$  [A] and  $\text{SnCl}_2 \cdot 2\text{H}_2\text{O}$  [B] in the molar ratio 0.5:0.5 M to 150ml of deionized water under magnetic stirring. 0.2M of urea was added to the above solution under continuous stirring for an hour. Next the mixed solution was transferred into a Teflon lined autoclave and treated at  $180^\circ\text{C}$  for 3 hours. Finally, the product obtained was washed with distilled water and acetone to remove unexpected ions and dried at  $200^\circ\text{C}$  in air. Other samples were prepared by the similar procedure by just changing the molar ratios of the

precursors A and B as [0.75:0.25] and [0.25:0.75] respectively.

Microstructure analysis were performed using X-ray diffraction (XRD) and Scanning electron microscopy (SEM). For the XRD, the Seifert 3003T/T X-ray diffractometer with  $\text{CuK}\alpha$  radiation in the  $2\theta$  range 20 to  $70^\circ$  was used. Surface morphologies of the samples were observed using a FEI Quanta FEG 200 Scanning electron microscope equipped with an EDAX detector. The electrical properties of the sample with respect to the cigarette smoke was measured by the Hitachi 3532-50 LCR Hitester.

### Results and discussion




Figure 1: XRD patterns of the as-prepared  $\text{SnO}_2$  –  $\text{CuO}$  composite particles annealed at  $200^\circ\text{C}$  that were initially synthesized using 3 different molar ratios

Figure 1 shows the XRD patterns of the as-prepared composites of  $\text{SnO}_2$ – $\text{CuO}$ . All of the tin oxide peaks match well with the standard  $\text{SnO}_2$  XRD pattern [JCPDS card file no: 88-0287] and are attributed to the tetragonal phase. The lattice constants thereby

calculated are tabulated (Table 1). The average crystallite size is related to the peak broadening. The average crystallite size of the tin dioxide particles was estimated by the Scherrer equation.

$$d = \frac{k\lambda}{\beta \cos\theta}$$

k is the shape factor equal to 0.89,  $\lambda$  is the X-ray wave length for Cu K $\alpha$  radiation (1.5418 Å),  $\theta$  is the Bragg diffraction angle and  $\beta$  is the full width at half maximum (FWHM) of the observed peak. It is also observed that the tin oxide peaks are more pronounced than the peaks of the cubic phase of the copper oxide [JCPDS card file no: 77-0199]. A few additional peaks of copper hydroxide can be accounted to be present


due to the low annealing temperature. We see that tin oxide begins crystallising earlier than copper oxide which requires higher annealing temperatures to completely oxidize [25]. Ming-you et al. also reports that CuO may have entered the crystal lattice thereby resulting in no distinct peaks. However, its presence in the composite can be confirmed by the EDAX analysis. From the tabulation (table 2) no other element is detected other than Sn and Cu for all three molar ratios.

SnO <sub>2</sub> [88-0287]	SnO <sub>2</sub> [0.25]:CuO[0.75]	SnO <sub>2</sub> [0.5]:CuO[0.5]	SnO <sub>2</sub> [0.75]:CuO[0.25]
<b>a = b = 4.737[Å]</b>	4.747 ± 0.089	4.772 ± 0.058	4.723 ± 0.045
<b>c = 3.186[Å]</b>	3.141 ± 0.080	3.186 ± 0.100	3.178 ± 0.083
<b>V = 71.49[Å<sup>3</sup>]</b>	70.77	72.54	70.88
<b>Crystallite size</b>	38.31nm	13.76 nm	16.01nm


Table 1: Lattice constants calculated for the distinct SnO<sub>2</sub> peaks for the 3 molar ratios.

SnO <sub>2</sub> : CuO	Atomic%		
	0.25:0.75	0.5:0.5	0.75:0.25
<b>Sn</b>	10.18	23.85	19.82
<b>Cu</b>	22.17	8.32	03.64
<b>O</b>	64.38	67.84	56.45


Table 2: Comparison of the Atomic % of the elements present in the 3 synthesized composites obtained by the EDX analysis Figure 2 (a), (b) and (c) shows the topographical images of the as-grown products of the Tin oxide-Copper oxide composites synthesized by the hydrothermal method. The surface morphology is observed to have flake –like appearance in all three cases though the overall morphology varies in each case.



*Figure 2a: HRSEM morphology for the SnO<sub>2</sub>-CuO composite with molar ratio 0.25:0.75*



*Figure 2b: HRSEM morphology for the SnO<sub>2</sub>-CuO composite with molar ratio 0.5:0.5*



*Figure 2c: HRSEM morphology for the SnO<sub>2</sub>-CuO composite with molar ratio 0.75:0.25*

The UV-Vis absorption spectra data of the composites are tabulated in table 3. The excited wavelength was obtained from the absorption spectra ( $\lambda_{ex}$ ). The band gap was thereby calculated using the formula  $E_g = \frac{hc}{\lambda}$ . The difference between band gap thereby calculated and the bulk band gap of the material was reported. A blue shift of the band gap is observed compared to the bulk materials in all three cases. As reported by Zhu et al. the blue shift indicates the onset of the absorptions that can be assigned to the direct transition of the electron in the sample [26].

Sample	Std	Cal	BG (eV)	BG Difference (eV)
	BG (eV)	$\lambda$ (nm)		
SnO <sub>2</sub>	0.25	308.08	4.04	0.44
	0.5	300.79	4.1	0.5
	0.75	334.09	3.7	0.1
CuO	0.75	1002.84	1.24	0.04
	0.5	979.04	1.27	0.07
	0.25	919.13	1.35	0.15

Table 3: Tabulation of the observed excitation wavelengths and the comparison between the bulk and calculated band gaps of SnO<sub>2</sub> and CuO for the different molar ratios.

Tobacco smoke is a varied, dynamic and reactive combination containing an estimated 5000 chemicals [27-29]. The main ingredients being nicotine, tar and carbon monoxide. Nicotine is a tertiary amine composed of a pyridine and a pyrrolidine ring, this along with carbon monoxide and tar are known to have independent effects on the human body. This toxic and carcinogenic blend is probably the most major source of toxic chemical exposure and chemically mediated disease in humans [30,31]. Literature has revealed that highly exposed non-smokers and active smokers share the same level of hair nicotine [32,33]. Thus there is an urgent need to monitor cigarette smoking in free living conditions. The responses of the composite materials are investigated by studying the change in the dielectric constant of the samples in ambient and cigarette smoke environment using a dielectric analyser. The as-prepared composites were pelletized under a pressure of 10 tonnes. The pelletized sample was loaded between two electrodes and then subjected to an alternating

voltage. The responses of the composites were studied in a sealed chamber. The electrical parameters at different frequencies in the presence of air are first noted, then a known volume (100ml) of cigarette smoke is injected into the chamber using a syringe and the parameters are noted again.

The A.C. conductivity is calculated using the formula  $\sigma_{ac} = 2\pi f \epsilon_0 \epsilon_r \tan \delta$ , where  $\epsilon_0 = 8.854 \times 10^{-12}$  F/m,  $\epsilon_r$  is the dielectric constant and  $\tan \delta$  is the dielectric loss. The figures 3(a),(b) and (c) graphically represent the A.C. conductivity of the composites at room temperature. It is observed that the A.C. conductivity  $\sigma_{ac}$  increases with increase in the frequency of the applied voltage. It is also observed that there is an increase in the A.C. conductivity of all the three composites when the smoke is introduced and the difference (at 5MHz) is tabulated below (Table 4). Comparing the readings of the composites with the pure samples, we note that there is an increase in the a.c. conductivity for the composites.

SnO <sub>2</sub> :CuO	[0.25:0.75]	[0.5:0.5]	[0.75:.25]	Pure SnO <sub>2</sub>	Pure CuO
Difference in $\sigma_{ac}$ in cigarette smoke and ambience (S/m)	$1.106 \times 10^{-5}$	$1.480 \times 10^{-5}$	$0.892 \times 10^{-5}$	$0.847 \times 10^{-5}$	$0.61 \times 10^{-5}$

Table 4: Difference in A.C. conductivity value of the composites

The a.c. conductivity response to cigarette smoke was recorded for continuously for 10 trials and the graphs were plotted as shown in figure 4(a), (b) and (c). It is observed that the conductivity remains a constant. The elementary sensing mechanism involved in metal oxide based gas sensors depends on the change in electrical conductivity as a result of the interaction process between the surface complexes such as O<sup>-</sup>, O<sup>2-</sup>, H<sup>+</sup> and OH<sup>-</sup> reactive chemical species and the

molecules of the gas that is to be sensed. Oxygen ions are adsorbed on the materials surface removing electrons from the bulk and thereby constructing a potential barrier that curbs the electron movement and conductivity. So when the material interacts with an oxidising or reducing gas, the concentration of the adsorbed oxygen changes causing a variation in the conductivity. Therefore we attribute this change in

conductivity as a measure of the gas concentration.  
[34].




Figure 3a: Plot of A.C. conductivity for the 0.25:0.75 ratio of the SnO<sub>2</sub>-CuO composite






Figure 3b: Plot of A.C. conductivity for the 0.5:0.5 ratio of the SnO<sub>2</sub>-CuO composite




Figure 3c: Plot of A.C. conductivity for the 0.75:0.25 ratio of the SnO<sub>2</sub>-CuO composite




Figure 4a: The a.c. conductivity vs time (s) at freq 5MHz, for the 0.25:0.75 ratio of the SnO<sub>2</sub>-CuO composite




Figure 4b: The a.c. conductivity vs time (s) at freq 5MHz for the 0.5:0.5 ratio of the SnO<sub>2</sub>-CuO composite




Fig 4c: The a.c. conductivity vs time (s) at freq 5MHz for the 0.75:0.25 ratio of the SnO<sub>2</sub>-CuO composite

### Conclusion

In summary, a facile hydrothermal method was used to synthesize flake-like tin oxide-copper oxide composites at different molar ratios. The XRD pattern demonstrates that the samples have peaks of both tin oxide with a tetragonal rutile structure and copper oxide in the cubic phase.

Furthermore from the electrical analysis, a noticeable change in the A.C. conductivity of the samples were observed in response to cigarette smoke. This technique of studying the dielectric parameters could open up novel ways of investigating gas sensing through device fabrication.

### Acknowledgement

The authors are grateful to Dr. C. Venkateswaran, Associate Professor, Department of Nuclear Physics, University of Madras, Chennai, and Dr. P. Sagayaraj and Dr. Jerome Das Associate Professors, Department of Physics, Loyola College, Chennai for their constant guidance and valuable suggestions.

### Reference

1. Reinskje Talhout, Thomas Schulz, Ewa Florek, Janvan Benthem, Piet Wester, Antoon Opperhuizen, Hazardous Compounds in Tobacco Smoke, *Int J Environ Res Public Health*, (2011); 8(2): 613–628.
2. Dangers of Second-Hand Smoke (Online) Available from [http://my.clevelandclinic.org/healthy\\_living/smoking/hic\\_dangers\\_of\\_secondhand\\_smoke.aspx](http://my.clevelandclinic.org/healthy_living/smoking/hic_dangers_of_secondhand_smoke.aspx) [Accessed on 1st Sept 2013]
3. H. Salehi, M. Aryadoust, M. Farbod, Electronic and Structural Properties of Tin Dioxide in Cubic Phase, *Iranian Journal of Science & Technology, Trans. A, Volume 34, Number A2* (2010)
4. B. Thangaraju, Structural and electrical studies on highly conducting spray deposited fluorine and antimony doped SnO thin films from SnCl precursor, *Thin Solid Films* 402 (2002) 71–78.
5. Zhu, J.; Tay, B. Y.; Ma, *Synthesis of mesoporous tin oxide on neutral surfactant templates*, *J. Mater. Lett.* 2006, 60, 1003.
6. Matthias Batzill, Ulrike Diebold, The surface and materials science of tin oxide, *Progress in Surface Science* 79 (2005) 47–154

7. Le DuyDuc, Dang ThiThanh Len , Nguyen Van Duy, Nguyen Duc Hoa, Nguyen Van Hieu, Single crystal cupric oxide nanowires: Length- and density-controlled growth and gas-sensing characteristics, *Physica E* 58 (2014) 16–23
8. Xue Wang, Chenguo Hu, Hong Liu, Guojun Du, Xiaoshan He, Yi Xi, Synthesis of CuO nanostructures and their application for nonenzymatic glucose sensing, *Sensors and Actuators B*, 144 (2010) 220–225
9. C. Batchelor-McAuley, Y. Du, G.G. Wildgoose, R.G. Compton, The use of cop-per(II) oxide nanorod bundles for the non-enzymatic voltammetric sensing of carbohydrates and hydrogen peroxide, *Sens. Actuators B: Chem.* 135 (2008) 230–235.
10. Z.J. Zhuang, X.D. Su, H.Y. Yuan, Q. Sun, D. Xiao, M.M.F. Choi, An improved sensitivity non-enzymatic glucose sensor based on a CuO nanowire modified Cu electrode, *Analyst* 133 (2008) 126–132
11. Patil Shiram B., More Mahendra A., Patil Arun V, Nanocrystalline Cobalt-doped SnO<sub>2</sub> Thin Film: A Sensitive Cigarette Smoke Sensor, *Sensors & Transducers Journal*, Vol. 134, Issue 11, November 2011, pp. 163-169
12. Hassan Karami, Investigation of sol-gel Synthesized CdO-ZnO Nanocomposite for CO Gas Sensing, *Int. J. Electrochem. Sci.*, 5 (2010) 720 – 730
13. Kong, J.; Franklin, N.; Zhou, C.; Chapline, M.; Peng, S.; Cho, K.; Dai, H. Nanotube molecular wires as chemical sensors. *Science* 2000, 287, 622-625.
14. Gopel, W.; Schierbaum, K. SnO<sub>2</sub> sensors current status and future prospects. *Sensor Actuator B-Chem* 1995, 26, 1-12.
15. Yamada, Y.; Seno, Y.; Masuoka, Y.; Yamashita, K. Nitrogen oxides sensing characteristics of Zn<sub>2</sub>SnO<sub>4</sub> thin film. *Sensor Actuator B-Chem* 1998, 49, 248-252.
16. Divya Haridas, K. Sreenivas, Vinay Gupta, Improved response characteristics of SnO<sub>2</sub> thin film loaded with nanoscale catalysts for LPG detection, *Sensors and Actuators B* 133 (2008) 270–275
17. A. Chaturvedi, V.N. Mishra, R. Dwivedi, S.K. Srivastava, Response of oxygen plasma-treated thick film tin oxide sensor array for LPG, CCl<sub>4</sub>, CO and C<sub>3</sub>H<sub>7</sub>OH, *Microelectronics Journal* 30 (1999) 259–264
18. Nguyen Van Hieu , Nguyen Anh Phuc Duc , Tran Trung , Mai Anh Tuan , Nguyen Duc Chien, Gas-sensing properties of tin oxide doped with metal oxides and carbon nanotubes: A competitive sensor for ethanol and liquid petroleum gas, *Sensors and Actuators B* 144 (2010) 450–456
19. Jinhuai Liu , Xingjiu Huang , Gang Ye , Wei Liu , Zheng Jiao , Wanglian Chao , Zhongbai Zhou , Zengliang Yu, H<sub>2</sub>S Detection Sensing Characteristic of CuO/SnO<sub>2</sub> Sensor, *Sensors* 2003, 3, 110-118
20. Xinyu Xue , Lili Xing, Yujin Chen, Songlin Shi, Yanguo Wang, Taihong Wang, Synthesis and H<sub>2</sub>S Sensing Properties of CuO-SnO<sub>2</sub> Core/Shell PN-Junction Nanorods, *J. Phys. Chem. C* 2008, 112, 12157–12160
21. Dang Thi Thanh Le, Do Dang Trung, Nguyen Duc Chinh, Bui Thi Thanh Binh, Hoang Si Hong, Nguyen Van Duy, Nguyen Duc Hoa, Nguyen Van Hieu, Facile synthesis of SnO<sub>2</sub>-ZnO core-shell nanowires for enhanced ethanol sensing performance, *Current Applied Physics*, Volume 13, Issue 8, October 2013, Pages 1637–1642
22. **Sun-Woo Choi, Jae Young Park and Sang Sub Kim, Synthesis of SnO<sub>2</sub>-ZnO core-shell nanofibers via a novel two-step process and their gas sensing properties, *Nanotechnology Vol. 20 46 (2009) 5603***
23. B.C.Yadav, Preeti Sharma, P.K.Khanna, Morphological and humidity sensing characteristics of SnO<sub>2</sub>-CuO, SnO<sub>2</sub>-Fe<sub>2</sub>O<sub>3</sub> and SnO<sub>2</sub>-Sb<sub>2</sub>O<sub>3</sub> nanoco oxides, *Bull. Mater. Sci.*, Vol. 34, No. 4, July 2011, pp. 689–698.
24. Satyendra Singh, Nidhi Verma, Archana Singh, B.C.Yadav, Synthesis and characterization of CuO-SnO<sub>2</sub> nanocomposite and its application as liquefied petroleum gas sensor, *Materials Science in Semiconductor Processing* Volume 18, February 2014, Pages 88–96
25. M. A. Ming-you, H. E. Ze-qiang, X. Z. Bing, H. Ke-long, X. Li-zhi, W. Xiang-ming, Synthesis and electrochemical properties of SnO<sub>2</sub>-CuO nanocomposite powders, *Trans. Nonferrous Met. Soc China*. 16 (2006) 791-794.
26. Z. Zhu, G. Ouyang, and G. Yang, Bandgap shift in SnO<sub>2</sub> nanostructures induced by lattice strain and coordination imperfection, *J. Appl. Phys.* 108 (2010) 083511
27. Hoffmann D.; Hoffmann I. Letters to the editor, tobacco smoke components. *Beitr. Tabakforsch.* Int. 1998, 18, 49-52.
28. Thielen A.; Klus H.; Muller, L. Tobacco smoke: unraveling a controversial subject. *Exp. Toxicol. Pathol.* 2008, 60, 141-156.

29. Borgerding M.; Klus H. Analysis of complex mixtures—cigarette smoke. *Exp. Toxicol. Pathol.* 2005, 57, 43-73.
30. Fowles J.; Dybing E. Application of toxicological risk assessment principles to the chemical constituents of cigarette smoke. *Tob. Control* 2003, 12, 424-430.
31. Ezzati M.; Lopez A.D. Estimates of global mortality attributable to smoking in 2000. *Lancet* 2003, 362, 847-852
32. Al-Delaimy W, Fraser T, Woodward A., Nicotine in hair of bar and restaurant workers, *N Z Med J.* (2001) 114(1127):80-3.
33. Dimich-Ward H., Gee H., Brauer M., Leung V., Analysis of nicotine and cotinine in the hair of hospitality workers exposed to environmental tobacco smoke, *JOccup Environ Med.* (1997) 39(10):946-8.
34. A. K. Singh, Microwave Assisted Growth of ZnO Nanorods and Nanopolydops Nanostructure Thin Films for Gas and Explosives Sensing, *Journal of Nanoparticles*, Volume 2013 (2013)